



Technical Data Sheet

Product	PLF100 SheenSeries										
Description	Pigmented polyurethane top-coats, fire retardant										
Color	White										
Chemical-physical Properties											
CODE	Density (Kg/l)				Density (lb/US gal)				Solid content %		
PLF100/1	1,235 ± 0,030				10,3 ± 0,3				68,5 ± 2		
PLF100	1,190 ± 0,030				9,9 ± 0,3				69,3 ± 2		
PLF100/6	1,250 ± 0,030				10,4 ± 0,3				70,2 ± 2		
	Viscosity (Ford 6 cup)					28 ± 2					
USAGE INDICATIONS											
Additional products					Quantities						
Hardener	TX50				In weight w/w %				50		
					In volume v/v %				62,5		
	Solid content %				24,3 ± 2						
Thinner	TZ33				In weight w/w %				30		
					In volume v/v %				42		
READY TO USE PRODUCT PROPERTIES (AVERAGE)											
	Solid content 1st + 2nd component (%)				54,3 ± 2						
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)				6 h						
	Viscosity (Ford 4 cup)				15 ± 2						
Code/Sheen	CODE				Sheen level EN ISO 2813 (angle measurement 60°)						
					applied micron: 100						
					Wet Mils: 3,9						
	PLF100/1				Sheen 70 ± 4						
	PLF100				Sheen 25 ± 2						
	PLF100/6				Sheen 10 ± 1						

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilvacoatings.com



Application		Quantities			
	Airless spray	gr/m² min-max:	95	-	105
		Wet Mils min-max	3,5	-	3,8
	Airmix spray	gr/m² min-max:	95	-	105
		Wet Mils min-max	3,5	-	3,8
	Curtain coater	gr/m² min-max:	95	-	105
		Wet Mils min-max	3,5	-	3,8
	Hand spray	gr/m² min-max:	95	-	105
Wet Mils min-max		3,5	-	3,8	
PRODUCT PROPERTIES AFTER APPLICATION					
Drying					
	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	24 h			
	Dust free	20 min			
	Touch dry	50 min			
	Hard dry	24 h			
	Hot air drying	(Time and temperature according to the drying system in use)			
Shelf life	12 months after production				
SPECIFIC WARNINGS	These products are part of the fire retardant certified coating cycle CLASSE 1 (Italian) according to UNI9796 (omologation n°MI2438PVI00002) regulation. Compliance tests were performed on 25sh top-coat, but are extended to 70sh, 10sh and relative blends These products are also part of the fire retardant coating cycle which complies with B-s1, d0 EUROCLASS EN 13501-1 requirement Pastel colors can be obtained adding approved fire resistant pigmented pastes colors (PZ331 - PZ332 - PZ333 - PZ340 - PZ344 - PZ336 - PZ338 - PZ339) CLASSE 1 (Italian) certification, UNI9796 compliant, requires the converter/paste ratio to be kept 70/30 after pastes addition, this is possible by adding the clear converter TOF800 SheenSeries (for further information see the technical data sheet)				

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilvacoatings.com



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.

On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features

Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 15-05-2024

Contact Details : Mick Kilsby - Mobile : 0410 635 011, Terry Taylor - Mobile : 0410 635 014

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilvacoatings.com