



Technical Data Sheet

Product	TO00 Gloss Series					
Description	Polyurethane Clear Topcoat					
Color	Clear					
Chemical-physical Properties						
CODE	Density (Kg/l)		Density (lb/US gal)		Solid content %	
TO00	0,975 ± 0,030		8,1 ± 0,3		45,0 ± 2	
TO01	0,975 ± 0,030		8,1 ± 0,3		43,0 ± 2	
TO02	0,975 ± 0,030		8,1 ± 0,3		43,0 ± 2	
TO03	0,975 ± 0,030		8,1 ± 0,3		45,0 ± 2	
TO04	0,986 ± 0,030		8,2 ± 0,3		45,0 ± 2	
TO05	0,992 ± 0,030		8,3 ± 0,3		46,0 ± 2	
TO06	0,990 ± 0,030		8,3 ± 0,3		47,0 ± 2	
TO07	0,987 ± 0,030		8,2 ± 0,3		48,0 ± 2	
(series average values)	Viscosity (EN ISO 2431) ISO 6 cup		33 ± 3			
USAGE INDICATIONS						
Additional products			Quantities			
Hardener	TX50	In weight w/w %			50	
		In volume v/v %			50,1	
	Solid content %		24,3 ± 2			
Thinner	TZ35	In weight w/w %			20	
		In volume v/v %			22	
READY TO USE PRODUCT PROPERTIES (AVERAGE)						
	Solid content 1st + 2nd component (%)		38,3 ± 2			
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)		4 h			
	Viscosity (Ford 4 cup)		16 ± 2			



Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)	
		applied micron: 150	
	TO00	Sheen	100 ± 5
	TO01	Sheen	72 ± 4
	TO02	Sheen	50 ± 3
	TO03	Sheen	35 ± 2
	TO04	Sheen	25 ± 2
	TO05	Sheen	15 ± 1
	TO06	Sheen	10 ± 1
	TO07	Sheen	5 ± 1
Application	Application method	Quantities	
	Airmix spray (for automatic plants)	gr/m ² min-max:	120 - 150
		Wet Mills min-max	4,9 - 6,1
	Hand spray	gr/m ² min-max:	120 - 150
		Wet Mills min-max	4,9 - 6,1
PRODUCT PROPERTIES AFTER APPLICATION			
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	18 h	
	Dust free	15 min	
	Touch dry	45 min	
	Hard dry	18 h	
	Additional products		Quantities
Properties	Good elasticity		
Hardener	TX50	In weight w/w %	50
		In volume v/v %	51,1
	Solid content %	23,4 ± 2	
Thinner	TZ35	In weight w/w %	20
		In volume v/v %	22
READY TO USE PRODUCT PROPERTIES (AVERAGE)			
	Solid content 1st + 2nd component (%)	38,0 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	5 h	
	Viscosity (Ford 4 cup)	16 ± 2	

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilva.it



Code/Sheen	Density (lb/US gal)	Sheen level EN ISO 2813 (angle measurement 60°)	
		applied micron: 150	
		Wet Mills: 5,9	
TO00		Sheen	100 ± 5
TO01		Sheen	77 ± 5
TO02		Sheen	53 ± 3
TO03		Sheen	40 ± 3
TO04		Sheen	30 ± 2
TO05		Sheen	22 ± 2
TO06		Sheen	15 ± 1
TO07		Sheen	5 ± 1
Application	Application method	Quantities	
	Airmix spray (for automatic plants)	gr/m ² min-max:	120 - 150
		Wet Mills min-max	4,9 - 6,1
	Hand spray	gr/m ² min-max:	120 - 150
Wet Mills min-max		4,9 - 6,1	
PRODUCT PROPERTIES AFTER APPLICATION			
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	18 h	
	Dust free	20 min	
	Touch dry	55 min	
	Hard dry	18 h	
	Additional products		Quantities
Properties	Good yellowing resistance		
Hardener	TX72	In weight w/w %	50
		In volume v/v %	51,1
	Solid content %	25,0 ± 2	
Thinner	TZ35	In weight w/w %	20
		In volume v/v %	22
	Solid content 1st + 2nd component (%)	38,5 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	3 h	
	Viscosity (Ford 4 cup)	16 ± 2	

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilva.it



Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)
		applied micron: 150
		Wet Mils: 5,9
	TO00	Sheen 100 ± 5
	TO01	Sheen 77 ± 5
	TO02	Sheen 53 ± 3
	TO03	Sheen 40 ± 3
	TO04	Sheen 30 ± 2
	TO05	Sheen 22 ± 2
	TO06	Sheen 15 ± 1
	TO07	Sheen 10 ± 1
Application	Application method	Quantities
	Airmix spray (for automatic plants)	gr/m ² min-max: 120 - 150 Wet Mils min-max 4,9 - 6,1
	Hand spray	gr/m ² min-max: 120 - 150 Wet Mils min-max 4,9 - 6,1
PRODUCT PROPERTIES AFTER APPLICATION		
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	18 h
	Dust free	15 min
	Touch dry	45 min
	Hard dry	18 h
Shelf life	18 months after production	

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilva.it



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.

On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 2015-06

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilva.it